

Product Description

Asian Paints Exterior Wall Primer is a water-based wall coating suitable for application on exteriors as an undercoat to exterior emulsions.

Performance Features & Benefits

Asian Paints Exterior Wall Primer has good opacity and whiteness, which helps improve the appearance of the emulsion topcoats. Exterior Wall Primer does not chalk and can be applied on freshly plastered surfaces that are adequately cured. Exterior Wall Primer does not require any water curing.

Recommended Usage

Asian Paints Exterior Wall Primer can be applied on a wide range of exterior cement plasters, exterior ceilings, asbestos sheets, concrete etc. as an undercoat.

Recommended Application

Cleaning: Ensure that the surface to be painted is free from any loose paint, dust or grease. Any previous growth of fungus, algae or moss needs to be removed thoroughly by vigorous wire brushing and cleaning with water.

Filling: Application of any kind of putty is not recommended. Surface imperfections such as holes, dents, cracks are to be filled only by using mixture of white cement & fine sand (in the ratio of 1:3).

Freshly-plastered surfaces must be allowed to cure completely. Apply as follows :

Product	Product Code	Thinner	Dilution % (by vol)	Application Viscosity (sec)	Recoating* Period (hrs)
Asian Paints Exterior Wall Primer (X2) Brush, Spray	0065	Water	🖌️ 90-110 🚮 40-45	🖌️ 15-18 🚮 33	4 hrs

*Recoat period is quoted for 25° C and 50% Relative Humidity, these may vary under different conditions.

🖌️ Brush 🚮 Spray

Exterior Wall Primer

X2

July 2003



Signature

Technical Data

a) Coverage**:	On normal masonry surface by brushing: 1 coat: 12 - 14 sq mtr / ltr
b) Drying Time:	Surface Dry time - 30 minutes
c) Gloss Levels/Sheen Levels:	NA
d) Flash Point (IS 101/1987, Part 1, Sec 6):	NA
e) Stability of Thinned Paint:	Use within 24 hrs.
f) Shelf-life:	3 years from date of manufacture in original tightly closed containers away from direct sunlight and excessive heat.

**Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness.

Precautions

- Kindly refer to the MSDS for Asian Paints Exterior Wall Primer.
- Do not apply when ambient temperature is less than 10° C or if the temperature might drop to this level within 4 hrs of application.
- Do not overthin or overextend the brush.
- Do not use Apcolite Universal Stainers or any other colourants.
- Stir well and strain before use.
- In coastal areas it is not recommended to leave the primer without the application of the topcoats for a long period of time.

Post Application Instructions

For the best performance of the paint, if left as such for a longer time before the application of the final coat, ensure that it is cleaned properly.

Safety Features

Non-flammable

Pack Sizes & Shade Range

Pack size availability:
1 ltr, 4 ltr, 20 ltr


Shade Range:
White

Contact us

For more information on our products and services, visit us at

 www.asianpaints.com,

else call

 **1600-22-5678**

(service available in select cities only)

Please note that this data sheet supersedes any previous versions.

asianpaints

Asian Paints (India) Limited, 6A, Shantinagar,
Santacruz (East), Mumbai - 400 055.