

# Asian Paints WoodTech Aquadur 2K Parquet for Interior



PRODUCT CODE: 5487

## ASIAN PAINTS WOODTECH AQUADUR 2K PARQUET BENEFITS



### EASY APPLICATION

Woodtech Aquadur 2K Parquet can be applied using roller, making it far easier to apply than conventional PU, which is always spray painted.



### CHILD SAFE

WoodTech Aquadur 2K Parquet has very low toxic metal content and is EN 71.3 compliant for low metal toxicity, which also makes it a child safe product.



### LOW VOC AND ODOUR

Woodtech Aquadur 2K Parquet surpasses European standards for low VOC and is virtually odourless, making it a green product in the complete sense.



### EXCELLENT WEAR RESISTANCE

WoodTech Aquadur 2K Parquet has superior film Wear Resistance making the product more durable.

## PRODUCT FEATURES

### DURABILITY



#### BEST IN CLASS

✓ HIGH

MEDIUM


LOW GLOSS

### COVERAGE

On smooth sanded wooden surface by Rolling

120-140 sq.ft/ltr/Coat

\*\* Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness.



### COLOURS AVAILABLE

#### CLEAR

Range of 9 attractive Translucent Asian Paints WoodTech Wood Stains & 6 Attractive WoodTech Aquadur Waterbased Wood Stains available to add/change colour.



### AVAILABLE PACKS



1 Ltr



4 Ltr

Woodtech Aquadur 2K Parquet Interior Kit (5487)- 1 Ltr, 4 Ltrs.

### FINISH



MATT SEMI GLOSS GLOSS HIGH GLOSS

## HOW TO APPLY

### PRE PAINTING STEPS



1. Sand the wooden surface along the grains using sand paper No. 180, and then 320 or 400. Wipe surface to clean off loose dust particles.



2. If the surface has dents, apply Woodtech Dent Filler with a putty knife over the dented area.



3. To add colour, apply Woodtech Wood Stains by ragging. Allow it to dry for 30 min to 120 minutes.

Note: 1. If required, apply Asian Paints Woodtech Wood Stains by ragging on sanded wooden surface and allow 30-120 minutes of drying time.  
2. Use Aquadur 2K Parquet as a Basecoat for Interior, as interior sealer coat. Do not use any other coat for sealing purpose.  
3. There is no maturation time.  
4. Asian Paints WoodTech wood stains should not be mixed with Asian Paints WoodTech Aquadur 2K Parquet basecoat.  
5. Asian Paints WoodTech Aquadur 2K Parquet basecoat must not be polluted with oil, varnish or the like and must not be sanded with steel wool between coats.  
6. Recoat period is quoted for 30°C and 75% relative humidity, these may vary under different conditions.  
7. Spraying air pressure 2.2 to 2.8 Kgs/sq.cm.  
8. Viscosity as measured by Ford Cup B4 at 30 Deg C

### PAINT APPLICATION PROCESS

APPLICATION	PRODUCT CODE	THINNER	DILUTION % (BY VOL)	VISCOSITY (SEC)	RECOATING PERIOD (HRS)
STEP 1 WOODTECH AQUADUR 2K PARQUET 1ST COAT ROLLER	5487	POTABLE WATER	Brush: 5-10 (If Required)	13-17 SECS.	16 HRS
SANDING Sand with emery paper 320 or 400 and wipe clean					
STEP 2 WOODTECH AQUADUR 2K PARQUET 2ND COAT ROLLER	5487	POTABLE WATER	Brush: 5-10 (If Required)	13-17 SECS.	5 HRS
SANDING Sand with emery paper 320 or 400 and wipe clean					
STEP 2 WOODTECH AQUADUR 2K PARQUET 3RD COAT ROLLER	5487	POTABLE WATER	Brush: 5-10 (If Required)	13-17 SECS.	5 HRS
SANDING Sand with Sand Paper No. 320 or 400 and Wipe Clean (Apply 4th Coat if required)					

# Asian Paints WoodTech Aquadur 2K Parquet for Interior




## HOW TO CHOOSE COLOUR



WOODSTAIN FANDECK



AQUADUR WOOD STAIN SHADE CARD



WOODTECH WOOD STAIN SHADE CARD

## ADDITIONAL INFORMATION

### POST PAINTING CARE

- ◆ For removing stains on tiles and metal surfaces, apply NC Thinner on the surface and wipe clean.
- ◆ If stains are difficult to remove, scrapping can be done after applying NC thinner on the stained area.
- ◆ Precautions need to be taken while spraying / brushing, like masking of adjoining areas with suitable material, as the stains may be difficult to remove if present on wood or coated wooden and wall surfaces.

### TECHNICAL DETAILS

- Drying time: Touch to Dry 60 minutes. Tack Free time 1.5 hours
- Flash point : (IS 101/1987, Part 1, Sec 6) : above 15°C (59° F)
- Stability of thinned paint: To be used within 4 hours
- Shelf Life: 12 Months from date of manufacture in original tightly closed container away from direct sunlight and extensive heat.

### PRECAUTIONS

- ◆ For optimum performance, Asian Paints WoodTech Aquadur 2K Parquet must be applied at a temperature between 20°C and 40°C and humidity not above 75%
- ◆ Do not over-thin and mix according to recommended ratios
- ◆ Stir well and strain before use.

### SAFETY FEATURES

- ◆ Kindly refer to the MSDS for Asian Paints Woodtech Aquadur 2K Parquet Interior which gives detailed information on safety measures while handling the paint.
- ◆ Store the product at ambient conditions in well ventilated locations and away from source of ignition and fire
- ◆ Use protective equipment like rubber/polyurathene gloves, safety goggles/glasses, face mask while handling the paint
- ◆ Avoid eye and skin contact. In both cases wash with soap and plenty of water. Get medical attention if irritation develops or persists.
- ◆ Do not inhale or ingest. In case of inhalation move to fresh air and seek medical attention if symptoms persist in both cases
- ◆ Dispose in land filling. Do not dispose in any drain or land filling
- ◆ No added Lead, Mercury or Chromium compounds